

ProRox® GR 903



ProRox GR 903 is a stone wool granulate with no additives. The granulate is especially suitable for the thermal insulation of cold boxes and air separation plants.

Product properties

Properties	Performance							Norms
Thermal conductivity	T_m (°C)	-180	-140	-100	-60	-20	20	EN 12667
	λ (W/mK)	0,015	0,018	0,022	0,027	0,033	0,039	
Corrosion resistance	Conforms to the stainless steel corrosion specification as per ASTM test methods C 692 and C 871 Trace quantity of water leachable chloride ions: ≤ 10 ppm							ASTM C795 EN 13468
Reaction to fire	Euroclass A1							EN 13501-1
	Surface burning characteristics; Flame spread=passed, Smoke development=Passed							ASTM E84 (UL 723)

Compliance

ProRox GR 903 Granulated Loose fill complies with the requirements as set by the Linde specification (Linde quality) and AGI Q 118 „Insulation work for refrigeration on industrial installations ; air separation plants.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.