

SeaRox® SL 740

SeaRox SL 720 is a semi-rigid, resilient slab made of stone wool.
The product can be supplied with reinforced alu foil or glass cloth.



Application

SeaRox SL 740 is used for comfort insulation.

Product properties

Properties	Performance		Norm	
Thermal conductivity	T (°C) λ (W/mK)	10 0,034	50 0,039	EN 12667
Nominal density	45 kg/m ³		EN 1602 / IMO	
Compressive strength	-		EN 826	
Fire classification	Non-combustible Approved for A constructions Low Flame-Spread Properties		Acc. IMO FTP code	
Water absorption (short term)	< 1 kg/m ²		EN 1609 AC	
Max. Application Temperature	Wool 250°C Facing 80°C		-	
Sound absorption directly mounted	α _w = 0,75 Thickness: 50 mm		ISO 354 (approximated) Evaluated after ISO 11 654	
Facings (on request)	Reinforced alu foil White glass cloth 210 g/m ² (GW 200)		IMO A.653(16) (low flame - spread)	

Dimensions

SeaRox SL 740

Thickness (mm): 25-100 Length (mm): 1000 Width (mm): 600

SeaRox SL 740 ALU

Thickness (mm): 25-100 Length (mm): 1000 Width (mm): 600

SeaRox SL 740 GW200

Thickness (mm): 25, 30, 50 Length (mm): 1000 Width (mm): 600

Local variations in standard dimensions might occur.



0575

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.