

SeaRox® SL 720

SeaRox SL 720 is a soft, lightweight slab (board) made of stone wool. Reinforced aluminium foil (ALU) and glass cloth (GW200, GW400, GW-A, ALU-G) facings are available upon request.



Application

SeaRox SL 720 is used for comfort insulation.

Product properties


Properties	Performance		Norm	
Thermal conductivity	T (°C) λ (W/mK)	10 0,035	50 0,045	EN 12667
Nominal density	32 kg/m ³		EN 1602 / IMO	
Compressive strength	-		EN 826	
Fire classification	Non-combustible Low Flame-Spread		Acc. IMO FTP code	
Water absorption (short term)	≤ 1 kg/m ²		EN 1609	
Max. Application Temperature	Wool 250°C Facing 80°C		-	
Sound absorption directly mounted	α _w = 0,75 Thickness: 50 mm		ISO 354 (approximated) Evaluated after ISO 11 654	
Facings (on request)	Reinforced alu foil		IMO A.653(16) (low flame - spread)	

Compliance

- SeaRox SL 720 complies to directive 2014/90/EU of 23 July on marine equipment (MED) and IMO 2010 FTP Code.
- Above product declarations are also applicable for product with optional facing.
- ROCKWOOL stone wool insulation is made from volcanic rock and complies with Note Q, regulation (EC) No. 1272/2008.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL A/S and cannot be used without a prior written consent.



0575



0097