

ProRox® WM 951

ProRox WM 951 is a lightly bonded stone wool insulation mat stitched on galvanized wire mesh using galvanized wire. Stainless steel mesh, stainless steel binding wire and/or reinforced aluminium foil facing is available upon request.

The wired mats are produced with an innovative, water repellent binder called WR-Tech™ to mitigate the risk of corrosion under insulation (CUI). WR-Tech ensures our stone wool maintains its superior water repellency even at elevated operating temperatures over the CUI range, while preserving the excellent thermal performance of the material during service.



Product properties



Properties	Performance												Norms
	T (°C)	50	100	150	200	250	300	350	400	500	600	640	
Thermal conductivity	λ (W/mK)	0,039	0,045	0,053	0,062	0,072	0,084	0,097	0,112	0,146	0,192	0,213	EN 12667
Maximum Service Temperature	640°C												EN 14706
Reaction to fire	Euroclass A1 Non-Combustible												EN 13501-1 IMO 2010 FTPC
Nominal density	80 kg/m ³												EN 1602
Corrosion resistance	Trace quantity of water leachable chloride ions: ≤ 10 mg/kg												EN 13468
Water absorption	$\leq 0,2$ kg/m ² $\leq 0,2$ kg/m ² (After 24 hrs. pre-heating at 250°C)												EN 1609
Water vapour diffusion resistance	$\mu = 1$												EN 14303
Influence on coating systems	Free from substances (e.g. silicone oil) that might impair surface wetting												VW 3.10.7
EN 14303 Designation code*	MW EN 14303-T2-ST(+)-640-WS1-CL10												EN 14303

* Thickness class declared under the load of 1000 Pa.

Compliance

ProRox WM 951 Wired Mats fully comply with the requirements as set by internationally recognized standards like EN14303, CINI 2.2.02, ASTM C592.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.